

TEXSELF 1,5

TEXSELF 1.5 is a self-adhesive, elastomeric mastic (SBS) waterproofing membrane, with a high mechanical performance polyethylene film finish on the upper side and an easily removable silicone film on the lower side.

ADVANTAGES

TEXSELF 1.5 is a membrane, in which the upper side acts as both a reinforcement and non-stick film. It is a high density, very stable, cross-laminated polyethylene film, with great tear resistance and magnificent mechanical properties.

- Extremely simple application: applies quickly, cleanly, and without the need for additional tools.
- Easy adherence to the substrate after applying the asphalt primer.
- Overlaps are carried out by simple contact and pressure.
- No blowtorch needed; TEXSELF 1.5 application only requires a brush, cutter and rubber roller.
- Safe to install; minimal risk of fires because no flame is used.
- Flexible membrane that easily absorbs the movements of the roof.



APPLICATION

- Waterproofing of underground walls
- Waterproofing of non-drinkable water tanks
- Details flashing in pitched roofs
- Reinforcement of waterproofing on pitched roofs subject to filtering as a result of rain and wind, or the accumulation of snow or ice on roofs, especially lowpitch roofs and on gables.
- It can be used as both a underlay or reinforcement layer for waterproofing systems with bituminous shingles.
- Capillarity barrier in partially buried walls to stop rising water
- As a vapour barrier in both conventional and deck roof systems.

REGULATIONS

- In accordance with the EN 13859-1 and EN 13696 standards. Certified with CE marking No. 0099/CPD/A85/0087
- Certified with No. 12/4905 "Texsa Damp-Proof Membranes" from the BBA (British Board of Agreement).
- Quality System in accordance with ISO:9001

Bituminous Waterproofing SBS

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.

INSTALLATION

- **SUPPORT:** The surface where it will be applied must be free of dust, loose or poorly adhered materials, oily or non-stick residue and any soil in general. It may be applied on concrete, wood and fretwork sheet supports; an adherence test must be conducted on all other surfaces.
- **Primer:** For better adherence of the membrane, apply EMUFAL I to the support, allowing to dry completely, approximately 24 hours. For flat and cohesive surfaces: metal, plastic, solid wood surfaces, priming may not be necessary. We recommend conducting a test beforehand in order to verify adherence.
- Remove the non-stick silicone film from the lower side and apply the membrane to the previously primed surface.
- Press the membrane against the substrate with a brush, from the center toward the edges, in order to prevent bubbles from forming.
- The overlap will be 8 cm, and will be carried out by pressing firmly (once the silicone film is removed) on the upper membrane with a roller.
- TEXSELF 1.5 must not be applied when temperature is below 5°C. If cold, windy, or humid, heat lightly.
- TEXSELF 1.5 must not be exposed to the elements; the membrane must be protected from the sun. The wear rate when exposed depends on the specific application conditions.
- Installation and measurements will be conducted in accordance with regulations of the UNE 104401 standard.



Bituminous Waterproofing SBS

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.

PACKAGING AND STORAGE

	TEXSELF 1,5
Kg/m ²	1,5 -0,1 +0,2
Length (m)	20
Width (m)	1
m ² /roll	20
m ² /pallet	460

Storage: Upright on pallet. Store in the original packaging in a dry and cool place, protected against weathering.

TECHNICAL PROPERTIES

CHARACTERISTICS	Test Method	Unit	TEXSELF 1,5
External fire behaviour	ENV 1187	-	--
Fire reaction	EN 13501-1:2002 (EN ISO 11925-2)	-	E
Watertightness	EN 1928:2000 (B)	-	Pass (10 kPa)
Maximum tensile strength (L x T)	EN 12311-1	N/50 mm	270 ± 70 270 ± 70
Elongation (L x T)	EN 12311-1	%	250 ± 50 220± 50
Root penetration resistance	EN 13948	-	NE
Static load resistance	EN 12730 (A)	kg	≥ 5
Impact resistance	EN 12691:2006	mm	NPD
Tear strength (nail) (L x T)	EN 12310-1	N	180 x 140 ± 50
Joint peel resistance	EN 12316-1	N/50 mm	100 ± 50
Joint shear resistance (L x T)	EN 12317-1	N/50 mm	270 x 270 ± 70
Artificial ageing by long-term exposure to high temperature	EN 1296 12 sem/weeks	EN 1109 / 1110	NPD
Artificial ageing by long term exposure to the combination of UV radiation, high temperature and water	EN 1297	EN 1850-1	NPD
Flexibility at low temperature	EN 1109	°C	≤ -15
Hazardous substances	--	--	PND

Bituminous Waterproofing SBS

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.

OTHER FEATURES

OTHER CHARACTERISTICS	Test Method	Unit	Value
Visible defects	EN 1850-1	-	Pass
Straightness	EN 1848-1	-	Pass (<20 mm/10 m)
Compound per area unit	EN 1849-1	kg/m ²	--
Thickness	EN 1849-1	mm	1,5 ± 0,2
Thickness in overlap	EN 1849-1	mm	-
Watertightness after stretching at low temperature	EN 13897	%	--
Dimensional stability	EN 1107-1	%	NE
Form stability under cyclic temperature change	EN 1108	mm	--
High temperature flow resistance	EN 1110	°C	≥ 80
Granule adhesion	EN 12039	%	NE
Water vapour transmission properties	EN 1931	μ	71800

Bituminous Waterproofing SBS

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.