

PAILLETTE ARDOISE

Our slate is made of crushed siliceous rock, which can be tinted , with a granulometry of between 0.5 and 2 mm.

APPLICATION

Customisation of waterproofing products is done with the systems TEXPUR and TEXTOP.

INSTALLATION

Sprinkle over finishing whilst the coating is still fresh.

Auxiliary Liquid Waterproofing

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.