

## MORTERPLAS SBS FP 4 KG

MORTERPLAS SBS FP 4 KG is a waterproofing membrane that is not self-protected, made of SBS elastomeric bitumen, reinforced with high density polyester felt (FP), and finished with a thermally bonded film on both the upper and lower side.

### ADVANTAGES

- Confers excellent mechanical properties to the membrane:
- Maximum puncturing resistance (static and dynamic)
- High tear resistance
- Good dimensional stability.



### APPLICATION

- It is especially recommended in applications where maximum puncturing resistance is needed.
- MORTERPLAS SBS FP can be applied in a double-layer system on non-trafficable and trafficable roofs for pedestrians and vehicles, with heavy protection.
- For single-layer systems, a membrane with a mass  $\geq 4$  kg will be used in systems in accordance with the DITs and local construction regulations.
- MORTERPLAS FP 4 kg can be applied as a membrane to ensure the watertightness of underground structures

Single and multi-layer flat roofs Walls.

### REGULATIONS

- In accordance with the EN 13707, EN 14695 and EN 13969-T standards. Certified with CE marking No. 0099/CPD/A85/0087
- Voluntary certification of the product with AENOR seal according to the same European standard.
- With DIT No. 516 Inverted roof systems "TEXLOSA® ROOFING SYSTEMS."
- With DIT No. 562/10 MORTERPLAS/MOPLAS ZERO slope
- With DIT No. 579/11 MORTERPLAS VEHICULAR TRAFFIC
- With DIT No. 580/11 UNDERGROUND STRUCTURES MORTERPLAS
- Quality System in accordance with ISO:9001

### Bituminous Waterproofing SBS

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.

## INSTALLATION

- **SUPPORT:** The surface must be dry, firm, even, clean and free of loose materials.
- It can be applied completely adhered, partially adhered or floating. · To adhere the membrane to the support, the support is primed with EMUFAL I. Once dry, use flame to adhere the membrane.
- The flame is applied as uniformly as possible (the greater the heat, the greater the retraction) along the width of the membrane without reaching the overlap, which will be done later, since it is important that the temperature be the same in every area. The flame should be applied until the anti-adherent film pore opens.
- The membranes are installed in such a way that no more than three membranes overlap at the same point.
- Overlaps are flame-bonded, with a minimum overlap of 8 cm.
- In the two-layer solution, the top membrane must be completely adhered to the bottom membrane, and it must be placed in the same direction so that the overlap lays approximately in the middle of the bottom membrane.
- Installation and measurements will be conducted in accordance with regulations of the UNE 104401 standard.



## Bituminous Waterproofing SBS

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.

## PACKAGING AND STORAGE

|                        | MORTERPLAS SBS FP 4 Kg |
|------------------------|------------------------|
| Kg/m <sup>2</sup>      | 4 -5/+10%              |
| Length (m)             | 10                     |
| Width (m)              | 1                      |
| m <sup>2</sup> /roll   | 10                     |
| m <sup>2</sup> /pallet | 270                    |

Storage: Upright on pallet. Store in the original packaging in a dry and cool place, protected against weathering.

## TECHNICAL PROPERTIES

| CHARACTERISTICS                                                                                        | Test Method                      | Unit           | MORTERPLAS SBS FP 4 kg |
|--------------------------------------------------------------------------------------------------------|----------------------------------|----------------|------------------------|
| External fire behaviour                                                                                | ENV 1187                         | -              | Broof(t1)              |
| Fire reaction                                                                                          | EN 13501-1:2002 (EN ISO 11925-2) | -              | E                      |
| Watertightness                                                                                         | EN 1928:2000 (B)                 | -              | Pass (10 kPa)          |
| Maximum tensile strength (L x T)                                                                       | EN 12311-1                       | N/50 mm        | 700 ± 200 450 ± 150    |
| Elongation (L x T)                                                                                     | EN 12311-1                       | %              | 45 ± 15 45 ± 15        |
| Root penetration resistance                                                                            | EN 13948                         | -              | NE                     |
| Static load resistance                                                                                 | EN 12730 (A)                     | kg             | ≥ 15                   |
| Impact resistance                                                                                      | EN 12691:2006                    | mm             | ≥ 1000                 |
| Tear strength (nail) (L x T)                                                                           | EN 12310-1                       | N              | 180 x 220 ± 50         |
| Joint peel resistance                                                                                  | EN 12316-1                       | N/50 mm        | NE                     |
| Joint shear resistance (L x T)                                                                         | EN 12317-1                       | N/50 mm        | 450 x 450 ± 150        |
| Artificial ageing by long-term exposure to high temperature                                            | EN 1296 12 sem/weeks             | EN 1109 / 1110 | NE                     |
| Artificial ageing by long term exposure to the combination of UV radiation, high temperature and water | EN 1297                          | EN 1850-1      | NE                     |
| Flexibility at low temperature                                                                         | EN 1109                          | °C             | ≤ -15                  |
| Hazardous substances                                                                                   | --                               | --             | PND                    |

## Bituminous Waterproofing SBS

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.

## OTHER FEATURES

| OTHER CHARACTERISTICS                              | Test Method | Unit              | Value              |
|----------------------------------------------------|-------------|-------------------|--------------------|
| Visible defects                                    | EN 1850-1   | -                 | Pass               |
| Straightness                                       | EN 1848-1   | -                 | Pass (<20 mm/10 m) |
| Compound per area unit                             | EN 1849-1   | kg/m <sup>2</sup> | 4,00 -5/+10%       |
| Thickness                                          | EN 1849-1   | mm                | --                 |
| Watertightness after stretching at low temperature | EN 13897    | %                 | --                 |
| Dimensional stability                              | EN 1107-1   | %                 | ≤ 0,4              |
| Form stability under cyclic temperature change     | EN 1108     | mm                | NE                 |
| High temperature flow resistance                   | EN 1110     | °C                | ≥ 100              |
| Granule adhesion                                   | EN 12039    | %                 | NE                 |
| Water vapour transmission properties               | EN 1931     | μ                 | 20000              |

## Bituminous Waterproofing SBS

TEXSA SYSTEMS SLU reserves the right to modify the information contained herein without prior notice and declines all liability in cases of errors produced due to inappropriate use of the product. The values shown in the technical sheet are the mean values from tests in our lab.